

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 443 270 A2

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **90314286.7**(51) Int. Cl.⁵: **C08L 67/04, C08G 63/08,
A61K 6/087**(22) Date of filing: **24.12.90**

A request for correction of pages 3 and 4 of the description and page 1 of the claims has been filed pursuant to Rule 88 EPC. A decision on the request will be taken during the proceedings before the Examining Division (Guidelines for Examination in the EPO, A-V, 2.2).

(30) Priority: **23.02.90 US 484692**(43) Date of publication of application:
28.08.91 Bulletin 91/35(84) Designated Contracting States:
CH DE ES FR GB IT LI NL SE


(71) Applicant: **MINNESOTA MINING AND
MANUFACTURING COMPANY**
3M Center, P.O. Box 33427
St. Paul, Minnesota 55133-3427(US)

(72) Inventor: **Oxman, Joel D., c/o Minnesota
Mining and
Manufacturing Company, 2501 Hudson Road
St. Paul, Minnesota 55144-1000(US)**
Inventor: **Ubel III, Andrew F., c/o Minnesota
Mining and
Manufacturing Company, 2501 Hudson Road
St. Paul, Minnesota 55144-1000(US)**

(74) Representative: **Baillie, Iain Cameron et al
c/o Ladas & Parry Isartorplatz 5
W-8000 München 2(DE)**

(54) **Blended polycaprolactone thermoplastic molding composition.**

(57) Thermoplastic molding compositions are made from a blend of high molecular weight and low molecular weight polycaprolactones. The blends have lower viscosity, and can have higher modulus, than a composition containing only high molecular weight polycaprolactone. The blends are especially useful for dental impressioning.

**Fig. 1****EP 0 443 270 A2**

FIELD OF THE INVENTION

This invention relates to thermoplastic molding compositions. It also relates to dental impression-taking, to the manufacture of dentures, crowns, bridges and other oral prosthetic devices, and to general-purpose modelmaking.

BACKGROUND OF THE INVENTION

High molecular weight poly (epsilon-caprolactone) (also known as "polycaprolactone") has been used as a thermoplastic molding compound for general-purpose modelmaking and dentistry. References describing polycaprolactone molding compositions include U.S. Pat. No. 4,835,203, Kokai (Japanese Published Pat. Appl.) Nos. 63-171554 and 63-270759, and TONE^R POLYMERS P-300 AND P-700 High Molecular Weight Caprolactone Polymers (1988 product literature of Union Carbide Corp.).

SUMMARY OF THE INVENTION

When the above-mentioned references refer to thermoplastic polycaprolactone molding compositions, they disclose compositions containing only a single grade of high molecular weight polycaprolactone, such as "TONE P-700" or "TONE P-767" 40,000 molecular weight polycaprolactone (Union Carbide Corp.). Hard tooth tissue impressions can be made using warmed high molecular weight polycaprolactone. However, the warm state viscosity is sufficiently high that soft tissue can be distorted and thus improperly modeled. The relatively viscous nature of warm high molecular weight polycaprolactone can also contribute to poor centric occlusion measurements in bite registration impressions. Lower molecular weight polycaprolactones lack rigidity in the cooled state, and may even be liquids at oral temperature. Insufficient rigidity can lead to a distorted impression and eventual poor fit of a denture, crown, bridge, or other prosthesis made from the impression.

The present invention provides a polycaprolactone molding composition, useful for dental impressioning and general-purpose modelmaking, the composition being solid at 38°C, and having a melting or softening point that comfortably can be withstood by oral tissues, characterized in that the composition contains a blend of high molecular weight and low molecular weight polycaprolactones.

The molding compositions of the invention have low viscosity in the warm state and good rigidity in the cool state, thus facilitating the making of improved impressions and models, especially when soft tissues and other pliable substances are modeled.

BRIEF DESCRIPTION OF THE DRAWING

FIG. 1 is a plot of viscosity vs. percent low molecular weight polycaprolactone for the compositions of Runs 1-22 of EXAMPLE 1;

FIG. 2 is a plot of storage modulus vs. percent low molecular weight polycaprolactone for the compositions of Runs 1-22 of EXAMPLE 1; and


FIG. 3 is a plot of storage and loss moduli for the composition of Run 2 of EXAMPLE 1.

DETAILED DESCRIPTION

For brevity, the term "molecular weight" in this specification refers to "weight average molecular weight". Although molecular weight can be determined in a variety of ways, with some differences in result depending upon the method employed, it is convenient to employ solution viscometry, or low angle laser light scattering with trifluoroethanol as the solvent. Standard sample isolation and preparation techniques should be observed.


The molding compositions of the invention contain both high molecular weight and low molecular weight polycaprolactone. The terms "high" and "low" are of course relative, but as used in this specification "high molecular weight polycaprolactone" refers to an epsilon-caprolactone homopolymer or copolymer whose molecular weight is as great as or greater than the lowest molecular weight substantially neat epsilon-caprolactone homopolymer heretofore used commercially for dental impressioning purposes. Thus, the high molecular weight polycaprolactones that can be used in the invention are believed to have a molecular weight of at least about 20,000, and preferably at least about 30,000.

The high molecular weight polycaprolactones preferably have the following formula:



where R¹ is an aromatic or a straight chain or branched aliphatic backbone, which can optionally contain one or more non-interfering substituents such as hydroxyl or amine groups, w is 1 if R¹ is hydrogen, and w otherwise has an average value of about 1 to about 4, M¹ is oxygen or -NR²- where R² is hydrogen or a non-interfering aromatic or aliphatic group, and the product of w times x is preferably at least about 250 and more preferably between about 250 and about 440.

The low molecular weight polycaprolactone is an epsilon-caprolactone homopolymer or copolymer whose molecular weight is less than the molecular weight of substantially neat epsilon-caprolactone homopolymer heretofore used commercially for dental impression purposes. Thus, the low molecular weight polycaprolactones that can be used in the invention are believed to have a molecular weight less than about 20,000, and preferably less than about 10,000. The low molecular weight polycaprolactones preferably have the formula:



where R³ is an aromatic or a straight chain or branched aliphatic backbone, which can optionally contain one or more non-interfering substituents such as hydroxyl or amine groups, y is 1 if R³ is hydrogen and y otherwise has an average value of about 1 to about 4, M² is oxygen or -NR⁴- where R⁴ is hydrogen or a non-interfering aromatic or aliphatic group, and the product of y times z is less than about 175. The product of y times z is preferably less than about 100, and more preferably is between about 3 and about 90.

As a further guide, the molecular weight ratio of high to low molecular weight polycaprolactones preferably is between about 9:1 to 1:9, and will depend in part on the intended use for the composition.

The polycaprolactone can contain property-modifying or cross-linkable functional groups (for example, hydroxyl, acrylate, methacrylate, epoxy, isocyanato, or vinyl groups) if desired. Preferred commercially available high molecular weight polycaprolactone polymers include the above-mentioned "TONE P-700" and "TONE P-767" polycaprolactones, the "CAPA" polycaprolactones "630" (30,000 molecular weight), "640" (40,000 molecular weight), "650" (50,000 molecular weight) and "656" (56,000 molecular weight) from Interlox, and the various high molecular weight polycaprolactones available from Daicell Chemical Industry Co., Ltd. Preferred commercially available low molecular weight polycaprolactone polymers include "TONE P-300" polycaprolactone (10,000 molecular weight), the "TONE" polycaprolactone diols "0200" (530 molecular weight), "0210" (830 molecular weight), "0230" (1,250 molecular weight), "0240" and "2240" (2,000 molecular weight), and "0250" (3,000 molecular weight), "TONE" polycaprolactone triols "0301" (300 molecular weight), "0305" (540 molecular weight) and "0310" (900 molecular weight) from Union Carbide Corp., as well as the "CAPA" polycaprolactone diols "203" (400 molecular weight) through "240" (4,000 molecular weight), "CAPA" polycaprolactone triols "304" (250 molecular weight) and "305" (540 molecular weight), and the "CAPA" polycaprolactone tetraol "316" (1,000 molecular weight) available from Interlox.

A preferred embodiment of our invention also contains a free-radically polymerizable resin and an initiator. Suitable free-radically polymerizable resins contain at least one ethylenically unsaturated monomer, oligomer, or polymer capable of undergoing addition polymerization. Such monomers include mono-, di- or polyfunctional acrylates and methacrylates such as methyl acrylate, methyl methacrylate, ethyl acrylate, isopropyl methacrylate, n-hexyl acrylate, styryl acrylate, allyl acrylate, glycerol diacrylate, glycerol triacrylate, ethyleneglycol diacrylate, diethyleneglycol diacrylate, triethyleneglycol dimethacrylate, 1,3-propanediol diacrylate, 1,3-propanediol dimethacrylate, trimethylolpropane triacrylate, 1,2,3-butanetriol trimethacrylate, 1,4-cyclohexanediol diacrylate, pentaerythritol triacrylate, pentaerythritol tetraacrylate, pentaerythritol tetramethacrylate, sorbitol hexacrylate, bis[1-(2-acryloxy)]-p-ethoxyphenyldimethylmethane, bis[1-(3-acryloxy-2-hydroxy)]-p-propoxyphenyldimethylmethane, tris-hydroxyethylisocyanurate triacrylate, beta-methacrylaminoethyl methacrylate, and mixtures thereof. Other suitable monomers include unsaturated amides such as methylene bis-acrylamide, methylene bis-methacrylamide, 1,6-hexamethylene bis-acrylamide and diethylenetriamine tris-acrylamide. Suitable oligomeric or polymeric resins include 200 to 500

molecular weight polyalkylene glycols, acrylated or methacrylated oligomers such as those of U.S. Pat. No. 4,642,126, acrylated urethanes such as "SARTOMER" 9503, 9504 and 9505 (Sartomer Corp.), "INTEREZ" CMD 8803, 8804 and 8805 (Radcure Specialties, Inc.), and "PHOTOMER" 6060, 6110, and 6160 (Henkel Corp.), as well as acrylated polyester oligomers such as "EBERCRYL" 830 (Radcure Specialties, Inc.).

5 Mixtures of free-radically polymerizable monomers, oligomers or polymers can be used if desired.

The free-radically polymerizable resin can if desired be cured using a conventional chemical initiator system, such as a combination of a peroxide and an amine. However, chemical cure systems typically require at least partial ingredient separation before use. The resin is preferably cured using a photoinitiator, optionally combined with a suitable photosensitizer or accelerator. The photoinitiator should be capable of
10 absorbing actinic radiation and generating free radicals for addition polymerization, at some wavelength between 200 and 800 nm. Suitable photoinitiators include alpha-diketones, monoketals of alpha-diketones or ketoaldehydes, acyloins and their corresponding ethers, chromophore-substituted halomethyl-s-triazines, chromophore-substituted halomethyl-oxadiazoles, arylodonium salts, and other commercially available ultraviolet ("UV") and visible light photoinitiators. Preferred photoinitiator systems include a mono or
15 diketone photoinitiator together with a suitable donor compound or accelerator, such as the systems described in U.S. Pat. Nos. 3,427,161, 3,756,827, 3,759,807, 4,071,424, 4,828,583, U.K. Pat. Specification No. 1,304,112, European Published Pat. Appl. No. 150,952 and Chem. Abs. 95:225704U.

The molding compositions of the invention can contain a wide variety of adjuvants depending upon the desired end use. Suitable adjuvants include solvents, diluents, plasticizers, pigments, dyes, inorganic or
20 organic fibrous or particulate reinforcing or extending fillers, thixotropic agents, indicators, inhibitors, stabilizers, UV absorbers, medicaments (e.g., leachable fluorides), biocides and the like. For custom tray applications, the molding composition preferably contains one or more fillers that maintain the composition's 60° C relaxation stress at equilibrium. Such trays preferably comprise a homogeneous blend of the polycaprolactones with a thixotropic filler (for example, submicron silica), the tray being shaped and sized
25 for use in the mouth, and the blend being a solid with a storage modulus (G') of at least about 10⁹ at 38° C and a manually-deformable semi-solid with a storage modulus between about 10⁶ and about 10¹⁰ at a temperature that comfortably can be withstood by oral tissues, and having a 60° C equilibrium relaxation stress (τ_e) greater than about 500 dyne/cm².

The amounts of high molecular weight and low molecular weight polycaprolactone, and the amounts of
30 other ingredients in the molding compositions of the invention, usually will be empirically selected. Selection should be based in part on the desired end use for the composition and the desired properties in the molten or softened ("warm") and solid ("cool") states. The warm state is characterized by an amorphous polycaprolactone microstructure, and by appreciable mass flow under moderate (hand) pressure at some temperature between body temperature (about 38° C) and the maximum temperature that comfortably can
35 be withstood by oral tissues. This maximum temperature is generally thought to be about 75° C, although a maximum of about 65° C is preferred. The cool state is characterized by a semi-crystalline polycaprolactone microstructure, and by minimal apparent mass flow under moderate pressure at temperatures below 38° C.

The warm and cool state properties permit the molding composition to be heated to a moderate temperature, manually shaped in the mouth while warm to conform to adjacent hard and soft oral tissue,
40 and cooled within the mouth to form a substantially rigid model.

The composition should remain substantially homogeneous (that is, it should not undergo macroscopic phase separation or filler sedimentation) and preferably should retain its desired properties even if repeatedly cycled between the warm and cool states. Thus the selection of ingredients can be guided in part by the desire to preserve homogeneity and thermoplastic reversibility.

45 We have found that compositions containing a blend of high and low molecular weight polycaprolactones can have both a higher modulus and a lower viscosity than a composition containing only one of the constituent polycaprolactones. In other words, the blend provides a synergistic combination of modulus and low viscosity. For dental impressioning, the relative amounts of high molecular weight and low molecular weight polycaprolactone are preferably selected so as to provide this synergistic combination. In general, to
50 attain such synergism the majority (by weight) of the polycaprolactone in the composition should be of the high molecular weight variety. For general-purpose modeling applications (where the solidified model may be subjected to less severe stresses than in dental impressioning), a synergistic increase in modulus may not be desired. Accordingly, somewhat lesser or greater quantities of low molecular weight polycaprolactone can be employed.

55 As a further guide, the preferred amounts of high and low molecular weight polycaprolactones, filler, polymerizable resin, and photoinitiator for dental impressioning are as follows:

	<u>Ingredient</u>	<u>Preferred Weight %</u>
5	High molecular weight polycaprolactone	10-90
	Low molecular weight polycaprolactone	10-90
10	Filler	0-70
	Polymerizable resin	0-50
	Photoinitiator	0-10

15

The ingredients in the molding composition can be blended by hand or by mechanical mixing. The ingredients preferably are warmed sufficiently to melt the polycaprolactones, but if desired can be mixed at lower temperatures. Any suitable mixing device can be used, including kettles equipped with a mechanical stirrer, extruders, rubber mills, and the like.

20 The molding composition can be put up in a variety of forms including preformed sheets, arch-shaped trays, ropes, buttons, woven or non-woven webs and the like. The composition can be shaped in a variety of ways including extrusion, injection molding and web processing using a coating knife or rollers. The composition can be sold unwrapped, loosely wrapped in a package, or packaged in tubes, syringes, flexible outer plastic skins, plastic or metal trays and the like. The composition can be extruded or cast in mono-, bi-, or poly-layers (for example, coplanar layers or layers arranged in core-shell fashion) in which each layer has a selected melting temperature, viscosity, modulus, stickiness, or other desired physical properties.

25 The molding composition can be converted from the cool state to the warm state by using a variety of energy sources. The composition can be immersed in a heated bath containing a suitable inert liquid (for example, water or a fluorochemical fluid) that will not dissolve or swell the composition in either its cool or warm states. The composition can also be softened using heat sources such as a hot air gun, hot plate, 30 conventional oven, infrared heater, or microwave oven. The composition can be encased in a plastic pouch, syringe or other container which is in turn heated (e.g. electrically), or subjected to one or more of the above-mentioned heating methods.

Transforming the molding composition from a warm state to a cool state requires loss of thermal energy 35 and can be carried out using a variety of cooling techniques. Cooling can take place under ambient conditions in the presence of air only. Cooling can be expedited using forced air, cold water, ice, or heat sinks such as chilled "cold packs" or flexible pouches containing low boiling inert liquids. Of particular interest for both dental and orthopedic applications are chilled cold packs in flexible pouches that have been 40 reshaped to match the contours of the model being cooled. For example, flexible pouches containing a chilled coolant can be fabricated in the shape of a full arch or quadrant and placed intraorally in contact with the warm molding composition. Analogously, a large coolant-filled blanket can be draped around an orthopedic casting or splint material prepared from a molding composition of the invention.

A simplified dental impression system can be prepared from the molding composition. Traditional 45 impression systems employ one or more low viscosity, flowable elastomeric materials such as an alginate, hydrocolloid, polyvinylsiloxane, polyether, or polysulfide contained in a fairly rigid adhesive-coated plastic or metal arch-shaped tray. The elastomeric material often is applied both to the dental tissue to be modeled and to the tray. The elastomeric material and surrounding tray are subsequently pressed against the dental tissue, and left in place until the elastomeric material has hardened. This traditional process involves several materials and steps, material waste and fairly lengthy set times.

50 The present invention permits impression using a monolayer or a bilayer thermoplastic molding composition. The monolayer model, or at least one layer of the bilayer model, is made from a molding composition of the invention. In a preferred embodiment, a flat sheet or a preformed arch-shaped tray is made from two coextruded thermoplastic layers. The physical properties of each layer emulate in part the properties of a conventional rigid tray and the elastomeric material respectively. At a suitable elevated 55 temperature the "tray" layer becomes a conformable, non-sticky melt (thereby permitting the warm tray layer to be hand-shaped into a custom tray configuration) and the "elastomer" layer exhibits good flow and low viscosity (thereby permitting the warm elastomer layer to flow around tooth structure and provide an accurate model). The warm bilayer construction provides easy placement, accurate impression, and

efficient use of materials. Cooling can take place rapidly, and in less time than is required to harden a conventional impression. Once cooled, the tray layer exhibits sufficient rigidity to discourage distortion of the impression during removal from the mouth or during subsequent handling. The elastomer layer provides stable, accurate modeling of hard and soft dental tissue.

5 If desired, a custom impression tray can be formed from a molding composition of the invention and filled with a conventional elastomeric impression material (for example, a silicone elastomer). By shaping the tray in the mouth before (or if desired, after) it is filled with elastomer, the tray volume and required amount of elastomer will be minimized.

10 The molding compositions of the invention have many other uses. For example, they can be used to prepare crowns, bridges, dentures, splints and pontics. They can also be used to prepare shapeable orthopedic casts and splints. They can be used in modelmaking, for example in tool and die-making. They will find general use in applications requiring rapid, accurate shaped object formation.

The following examples are offered to aid in understanding the invention and are not to be construed as limiting its scope. Unless otherwise indicated, all parts and percentages are by weight.

15

EXAMPLE 1

85 Parts "TONE P-767" (40,000 molecular weight) polycaprolactone and 15 parts "TONE P-300" (10,000 molecular weight) polycaprolactone were placed in an open vessel and heated in an oven at 80 °C until both components were fluid. The vessel was transferred to an 80 °C water bath and the mixture stirred until homogeneous. The resultant blend was poured onto polyester sheeting atop a horizontal platform. A second polyester sheet was placed atop the molten mass. A roller was used to form the blend into sheets of approximately 2-4 mm thickness. The sheets were transparent while warm and became opaque when cooled under a stream of cold water.

25 Using a similar procedure a control composition (containing 100% "TONE P-767" polycaprolactone) and twenty additional high molecular weight/low molecular weight polycaprolactone blends were prepared. Set out below in TABLE I are the types, amounts and molecular weights of the high molecular weight ("HMW") and low molecular weight ("LMW") polycaprolactones in each composition, and several physical properties for each composition. Warm state viscosity was measured at 65 °C using a rheometric dynamic analyzer (Rheometrics Inc.) operating at 20% maximum strain and a 1 radian/second strain rate. Cool state storage modulus was measured at 30 °C on the rheometric dynamic analyzer, operated at 1.4% maximum strain and a 10 radian/second strain rate.

30 Dimensional stability was evaluated using a modified version of American Dental Association (ADA) Test Specification No. 19 (J.A.D.A., 94, 733 (1977)). Each molding composition was heated to 80 °C until molten and poured onto the ruled die prescribed in the Test Specification. A transparent rigid plate was placed atop the molten composition, and secured to the ruled die with a clamp. The molten composition was allowed to cool for 5 minutes at room temperature. The clamp and solidified molding composition were removed from the die. The resulting model was stored at 23±1 °C and 50±5% relative humidity for 24 hours. Dimensional stability was determined by comparing the distances between the ruled lines on the model and on the ruled die using an optical comparator.

40 Compression set was evaluated using a modified version of ADA Test Specification No. 19. Each molding composition was heated to 80 °C until molten, and transferred to the standard compression set cylindrical mold prescribed in the Test Specification. The mold endplates were clamped into place and the mold and its contents cooled in a 22 °C water bath for 5 minutes. The resulting solidified model was removed from the mold. Each model was axially compressed 1.0 mm for 30 seconds using a metered screw clamp. The clamp was released and a measurement of permanent deformation recorded one minute later. The percentage change in cylinder height was calculated to determine compression set.

45 Strain-in-compression was evaluated using a modified version of ADA Test Specification No. 19. Cylindrical models were prepared according to the compression set test described above. The cylinder height was measured, a 1.125 kg mass was placed atop the cylinder, and a second height measurement was recorded thirty seconds later. The percentage change in cylinder height was calculated to determine strain-in-compression.

55 Inlay accuracy was evaluated by heating each molding composition to 65 °C, and using the resulting molten compositions to make an impression of a Class II MOD preparation on the lower left first molar of a "TYPODONT" model (Columbia Dentoform Corp.). The molten compositions were applied evenly to the second premolar, the prepared first molar and the second molar, and pressed into place using finger pressure while in the transparent, molten state. Each composition was cooled for 60 seconds using a stream of cold water and then removed from the TYPODONT model yielding a completed opaque

impression. A standard gypsum "stone" model was poured in each impression. The hardened stone model was easily removed from the impression by slightly warming the impression to about 60° C in a water bath. An inlay was fabricated on each stone model in the following manner. A thin film of room-temperature vulcanizing silicone ("IMPRINT", 3M) was applied to the MOD preparation on the stone model and allowed to cure. Light curable restorative material ("SILUX PLUS", 3M) was tamped into the MOD preparation and shaped and carved to provide proper fit and anatomy. The restorative material was irradiated with a visible light curing lamp ("VISILUX 2", 3M) for 60 seconds. The resulting photohardened inlays were removed from the stone model and evaluated for overall fit on the original TYPODONT model preparation. Inlays were rated by two evaluators as providing excellent (" + +"), acceptable (" +"), or unacceptable (" -") fit.

10

15

20

25

30

35

40

45

50

55

TABLE I

Run No.	HMW PCL		LMW PCL		Viscosity, 65°C, Kilopoise	Modulus, 30°C, dyne/cm ² x 10 ⁸	Dimensional stability, % shrinkage	Compression set, %	Strain in compression, Inlay fit	
	Type	Parts	Type	Parts					%	fit
1	P-767 ¹	100	None	0	84.0	8.2	0.70	0.98	0.38	-
2	"	85	P-300 ²	15	21.6	13.1	0.86	1.03	0.25	-
3	"	70	"	30	19.3	12.4	0.87	1.25	0.45	-
4	"	55	"	45	7.8	7.2	0.62	1.05	0.30	++
5	"	85	0260 ³	15	43.3	NM ⁴	0.89	0.95	0.33	+
6	"	70	"	30	8.9	14.5	0.93	0.95	0.30	++
7	"	55	"	45	7.2	NM ⁴	0.83	1.10	0.30	+
8	"	85	0240 ⁵	15	17.6	13.0	0.96	1.03	0.35	+
9	"	70	"	30	10.2	14.5	0.88	1.00	0.43	+
10	"	55	"	45	5.3	13.3	0.95	0.93	0.45	++
11	"	85	2240 ⁶	15	8.0	12.4	0.87	0.85	0.75	++
12	"	70	"	30	13.1	12.4	0.71	1.03	0.38	-
13	"	55	"	45	2.6	9.3	0.72	0.98	0.35	++
14	"	85	0230 ⁷	15	33.7	11.3	0.91	0.83	0.43	+
15	"	70	"	30	16.3	9.0	0.78	0.90	0.40	+/++
16	"	55	"	45	6.2	11.3	0.58	0.78	0.45	-
17	"	85	0305 ⁸	15	11.6	7.9	0.71	0.75	0.48	++
18	"	70	"	30	19.7	6.2	0.77	0.80	0.55	++
19	"	55	"	45	7.3	3.1	0.74	0.83	0.48	++

TABLE I (Continued)

Run No.	HMW PCL		LMW PCL		Viscosity, 65°C, Kilopoise		Modulus, 30°C, dyne/cm ² x 10 ⁸		Dimensional stability, % shrinkage		Compression set, %		Strain in compression, Inlay fit	
	Type	Parts	Type	Parts										
20	"	85	0200 ⁹	15	34.7	10.9	0.82	0.90	0.30	-				
21	"	70	"	30	7.9	7.5	0.75	0.98	0.78	+ / ++				
22	"	55	"	45	84.0	4.0	0.66	0.98	0.63	+ / ++				

- 1 "TONE P-767" 40,000 molecular weight polycaprolactone (Union Carbide Corp.).
- 2 "TONE P-300" 10,000 molecular weight polycaprolactone (Union Carbide Corp.).
- 3 "TONE 0260" 3,000 molecular weight polycaprolactone (Union Carbide Corp.).
- 4 "NM" = Not measured.
- 5 "TONE 0240" 2,000 molecular weight polycaprolactone (Union Carbide Corp.).
- 6 "TONE 2240" 2,000 molecular weight polycaprolactone (Union Carbide Corp.).
- 7 "TONE 0230" 1,250 molecular weight polycaprolactone (Union Carbide Corp.).
- 8 "TONE 0305" 540 molecular weight polycaprolactone (Union Carbide Corp.).
- 9 "TONE 0200" 530 molecular weight polycaprolactone (Union Carbide Corp.).

The above data illustrates the extent to which a reduction in warm state viscosity and an increase in cool state modulus can be attained, by blending low molecular weight polycaprolactone with high molecular weight polycaprolactone. The data is further illustrated in FIGS. 1 and 2. FIG. 1 shows an unsmoothed plot of viscosity at 65°C vs. percent low molecular weight polycaprolactone for Runs 1-22 of TABLE I. Curves A through G connect the data points for blends containing the "TONE" low molecular weight polycaprolac-

tones "0260", "0230", "0200", "P-300", "0240", "0305", and "2240", respectively. As shown in FIG. 1, even relatively small additions of low molecular weight polycaprolactone provide a substantial viscosity reduction. For example, addition of only 15% "TONE P-300" (10,000 molecular weight) polycaprolactone provides a 74% viscosity reduction. The resulting blend was a free-flowing, homogeneous, transparent pourable liquid at 65 °C, which readily flowed into fissures and other interstices in a mold.

Referring now to FIG. 2, an unsmoothed plot of modulus at 30 °C vs. percent low molecular weight polycaprolactone is shown for Runs 1-22 of TABLE I. The curves are labeled as in FIG. 1. With the possible exception of the blends containing "TONE 0305" (540 molecular weight) polycaprolactone (whose modulus was not measured in the region between 0 and 15% low molecular weight polycaprolactone), the remaining blends all exhibited increased modulus at appropriate low molecular weight polycaprolactone addition levels. This increase in modulus is manifested by reduced flexibility and greater handling strength in the cooled state. As shown in FIG. 2, even relatively small additions of low molecular weight polycaprolactone provide a substantial modulus increase. For example, addition of only 15% "TONE P-300" polycaprolactone provides a 60% modulus increase. The resulting blend formed a stiff, handleable opaque white sheet at 30 °C.

Several of the molding compositions shown in TABLE I should meet the ADA's requirements for impression materials, and should permit the fabrication of excellent inlays and other dental prosthetic devices.

EXAMPLE 2


Rectangular 2.5x13x33 mm torsion bars were cast from the molding composition of Run 2 of EXAMPLE 1, and evaluated for storage and loss moduli (G' and G'', respectively) using a rheometric dynamic analyzer operated at 1.4% maximum strain and a 10 radian/second strain rate. FIG. 3 contains a plot of the modulus measurements between 32 °C and 70 °C. The data shows that the composition had a sharp melting point at temperatures that would be acceptable in the mouth. At body temperature (about 38 °C), the molding composition exhibits solidity, usefully high modulus, and desirably low plasticity.

Although this invention has been described using certain illustrative examples, it should be understood that the invention is not limited to the specific exemplary embodiments shown in this specification.


The words "CAPA", "EBERCRYL", "IMPRINT", "INTEREZ", "PHOTOMER", "SARTOMER", "SILUX", "TONE", "TYPODONT" and "VISILUX" are trademarks.

Claims

1. A polycaprolactone molding composition, the composition being solid at 38 °C, and having a melting or softening temperature that comfortably can be withstood by oral tissues characterized in that the composition contains a blend of high molecular weight and low molecular weight polycaprolactones.
2. A composition according to claim 1, wherein the high molecular weight polycaprolactone has a molecular weight greater than 30,000, and the low molecular weight polycaprolactone has a molecular weight less than 10,000.
3. A composition according to any preceding claim, characterized in that at least one of the high molecular weight and low molecular weight polycaprolactones comprises epsilon-caprolactone homo-polymer.
4. A composition according to any preceding claim, characterized in that the high molecular weight polycaprolactone has the formula:



where R¹ is an aromatic or a straight chain or branched aliphatic backbone, w is 1 if R¹ is hydrogen, and w otherwise has an average value from 1 to 4, M¹ is oxygen or -NR²- where R² is hydrogen or a non-interfering aromatic or aliphatic group, and the product of w times x is greater than 175, and the low molecular weight polycaprolactone has the formula:



5

where R³ is an aromatic or a straight chain or branched aliphatic backbone, y is 1 if R³ is hydrogen and y otherwise has an average value from 1 to 4, M² is oxygen or -NR⁴- where R⁴ is hydrogen or a non-interfering aromatic or aliphatic group, and the product of y times z is less than 175.

- 10 5. A composition according to any preceding claim, further characterized in that the composition contains at least one ethylenically unsaturated monomer, oligomer or polymer capable of undergoing free-radical polymerization, together with a suitable photoinitiator.
- 15 6. A composition according to any preceding claim, characterized in that the amount of low molecular weight polycaprolactone is sufficient to increase the composition's cool state storage modulus and lower the composition's warm state viscosity.
- 20 7. A composition according to any preceding claim, further characterized by containing 10 to 90 weight percent high molecular weight polycaprolactone, 10 to 90 weight percent low molecular weight polycaprolactone, 0 to 70 weight percent filler, 0 to 50 weight percent free-radically polymerizable resin, and 0 to 10 weight percent photoinitiator.
- 25 8. A composition according to any preceding claim, further characterized by being in the form of a dental crown or bridge.
9. A composition according to any preceding claim, further characterized by being in the form of a male or female mold of a tooth or teeth.
- 30 10. A composition according to any preceding claim, further characterized in that the composition comprises at least one layer of a multi-layer thermoplastic molding composition.


35


40


45

50

55

**Fig. 1**

**Fig. 2**

**Fig. 3**

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets




(11) Publication number:

0 443 270 A3

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **90314286.7**(51) Int. Cl.⁵: **C08L 67/04, C08G 63/08,
A61K 6/087, A61K 6/10**(22) Date of filing: **24.12.90**(30) Priority: **23.02.90 US 484692**(43) Date of publication of application:
28.08.91 Bulletin 91/35(84) Designated Contracting States:
CH DE ES FR GB IT LI NL SE(88) Date of deferred publication of the search report:
12.08.92 Bulletin 92/33(71) Applicant: **MINNESOTA MINING AND
MANUFACTURING COMPANY**
3M Center, P.O. Box 33427
St. Paul, Minnesota 55133-3427(US)(72) Inventor: **Oxman, Joel D., c/o Minnesota
Mining and
Manufacturing Company, 2501 Hudson Road**
St. Paul, Minnesota 55144-1000(US)
Inventor: **Ubel III, Andrew F., c/o Minnesota
Mining and
Manufacturing Company, 2501 Hudson Road**
St. Paul, Minnesota 55144-1000(US)(74) Representative: **Baillie, Iain Cameron et al**
c/o Ladas & Parry, Altheimer Eck 2
W-8000 München 2(DE)(54) **Blended polycaprolactone thermoplastic molding composition.**

(57) Thermoplastic molding compositions are made from a blend of high molecular weight and low molecular weight polycaprolactones. The blends have lower viscosity, and can have higher modulus, than a composition containing only high molecular weight polycaprolactone. The blends are especially useful for dental impressing.

**Fig. 1****EP 0 443 270 A3**



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 90 31 4286

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	PATENT ABSTRACTS OF JAPAN vol. 13, no. 273 (C-609)22 June 1989 & JP-A-01 068 252 (DAICEL CHEM IND LTD) 14 March 1989 * abstract *	1,3,4,6, 7,9	C08L67/04 C08G63/08 A61K6/087 A61K6/10
X	WORLD PATENTS INDEX LATEST Week 9004, Derwent Publications Ltd., London, GB; AN 90-025843 & JP-A-01 303 146 (DAICEL CHEM IND KK) 7 December 1989 * abstract *	1,3,4,6, 7,9	
A	EP-A-0 169 037 (JOHNSON & JOHNSON) * claim 1 *	1,7	
P,X	WORLD PATENTS INDEX LATEST Week 9015, Derwent Publications Ltd., London, GB; AN 90-111102 & JP-A-02 060 672 (DAICEL CHEM IND KK) 1 March 1990 * abstract *	1,3,4,6, 7,9	TECHNICAL FIELDS SEARCHED (Int. Cl.5)
P,X	CHEMICAL ABSTRACTS, vol. 113, no. 26, Columbus, Ohio, US; abstract no. 237872A, & JP-A-02-060642(DAICEL CHEM. IND LTD) 01.03.1990 * abstract *	1,3	C08L A61K
The present search report has been drawn up for all claims			
Place of search BERLIN		Date of completion of the search 01 JUNE 1992	Examiner VOIGTLANDER R.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	

EPO FORM 1503 (01.82) (P0401)